

TECHNICAL DATA**AUTOGLOW DEMPUL PLASTIC BPO/MERAH****DP10000000****Chemical base : Unsaturated Polyester (UP)**

Colour	DP10000000 : Light Grey HD101 Hardener : Red																											
Material	Polyester Putty : DP10000000 Hardener Red Pasta (BPO) : HD101																											
General Qualities	<ul style="list-style-type: none"> - Good adhesion on metal surface - Easy to apply on Zinc Plate, Aluminum, Wood and Fiberglass - Heat Resistant up to 100°C for 30 minutes - Wet Sanding system (can't Dry Sanding by machine) 																											
Persiapan Permukaan	<table border="0" style="width: 100%;"> <tr> <td style="width: 33%;">Cleaning</td> <td style="width: 33%;">Sanding</td> <td style="width: 33%;">Next Cleaning</td> </tr> <tr> <td>Old Paint</td> <td>CS20 - 0305 P 80 - 150</td> <td>CS20 - 0305</td> </tr> <tr> <td>OEM Spare Parts</td> <td>CS20 - 0305 P 150 - 240</td> <td>CS20 - 0305</td> </tr> <tr> <td>TPA Acrylic Lacquer</td> <td>Don't use</td> <td></td> </tr> <tr> <td>Steel Plate</td> <td>CS20 - 0305 P 80 - 150</td> <td>CS20 - 0305</td> </tr> <tr> <td>Zinc Plated Steel</td> <td>CS20 - 0305 P 180 - 240</td> <td>CS20 - 0305</td> </tr> <tr> <td>Aluminium</td> <td>CS20 - 0305 P 80 - 150</td> <td>CS20 - 0305</td> </tr> <tr> <td>Fiberglass</td> <td>CS20 - 0305 P 150 - 240</td> <td>CS20 - 0305</td> </tr> <tr> <td>Wood</td> <td>CS20 - 0305 P 80 - 150</td> <td>CS20 - 0305</td> </tr> </table> <p>CS20 - 0305 = Silicon Remover</p>	Cleaning	Sanding	Next Cleaning	Old Paint	CS20 - 0305 P 80 - 150	CS20 - 0305	OEM Spare Parts	CS20 - 0305 P 150 - 240	CS20 - 0305	TPA Acrylic Lacquer	Don't use		Steel Plate	CS20 - 0305 P 80 - 150	CS20 - 0305	Zinc Plated Steel	CS20 - 0305 P 180 - 240	CS20 - 0305	Aluminium	CS20 - 0305 P 80 - 150	CS20 - 0305	Fiberglass	CS20 - 0305 P 150 - 240	CS20 - 0305	Wood	CS20 - 0305 P 80 - 150	CS20 - 0305
Cleaning	Sanding	Next Cleaning																										
Old Paint	CS20 - 0305 P 80 - 150	CS20 - 0305																										
OEM Spare Parts	CS20 - 0305 P 150 - 240	CS20 - 0305																										
TPA Acrylic Lacquer	Don't use																											
Steel Plate	CS20 - 0305 P 80 - 150	CS20 - 0305																										
Zinc Plated Steel	CS20 - 0305 P 180 - 240	CS20 - 0305																										
Aluminium	CS20 - 0305 P 80 - 150	CS20 - 0305																										
Fiberglass	CS20 - 0305 P 150 - 240	CS20 - 0305																										
Wood	CS20 - 0305 P 80 - 150	CS20 - 0305																										
Finishing Material	<ul style="list-style-type: none"> - Epoxy Primer Filler Fast Dry PR206 - Nitrocellulose PGM6/PGS6 - Line - PU Acrylic Enamel DA21 - Line - Base Coat EF / DF - Line - Clear PU CC704/CC2010/CC2080 CC10 																											
Additional Tips	<ul style="list-style-type: none"> - Remove old paints, rust, dirt, oil etc. from the surface - Mix well putty with 2 - 3% BPO hardener - Apply a thin layer then build it - Sanding after complete drying 																											
Usage	As Putty																											
Mixing Ratio	100 parts by weight DP10000000 2-3 parts by weight HD101																											
Pot Life (30°C)	8 - 10 min																											
Sanding	Wet Sanding System, 30-40 min after finish layer P 180 - 240																											
Attention	This package contains volatile and flammable solvent and when using this product need adequate ventilation. It is recommended to wear safety tools																											