

Description

MASTERKYD TC 751 is a high solid, high gloss synthetic enamel alkyd paint. It is specially formulated to decorate and protect for exterior and interior surfaces. The product is flexible and resistant to salt water and spillage of mineral oil and other aliphatic hydrocarbons.

Key Features

- High gloss
- High solid
- Lead and Chrome-free

Recommended Use

As finishing coat for alkyd systems on exterior and interior steel and woodwork in mildly to moderately corrosive environment.

Product Data

Properties

Type	: Alkyd Topcoat
Solid Volume	: 48 ± 2%
Specific gravity	: 1.10 kg/l (calculated)
Dry film thickness	: 30 – 50 µm
Wet film thickness	: 65 – 105 µm
Spreading rate theoretical	: 16 – 9.6 m ² /l
Finish	: High Gloss (85% – 100%)
Color	: According to the color card

Packaging Size

5 Liter
20 Liter

Application Data

Substrate & Surface Preparation

- General
To secure lasting adhesion to the subsequent product all surfaces shall be clean, dry and free from any contamination that can reduce adhesion via SSPC-SP1 solvent cleaning.
- Previously painted surfaces
All previously painted surfaces should be cleaned thoroughly to remove surface contamination. Rinse well and allow to dry. Scrape loose, scaly, peeling paint and sand the edges smooth, remove any rust and scale from ferrous metal. If the paint is glossy, sand to dull the surface. Test for compatibility with existing coatings.

Mixing

Single pack. Stir well before use.

Thinner/Cleaning

Thinner 2

Application Method

- Airless Spray
 - Pump Ratio : 30 : 1 (minimum)
 - Tip Size : 0.017 – 0.031 inch
 - Fluid Output : 1.5 – 2.5 litres/min

- Pressure Output : 1500 – 3000 psi
- Filter Size : 60 mesh
- Brush & Roller may be used only for stripe coating and small areas

Application Condition

Condition	Substrate Temp.	Ambient Temp.	Humidity
Minimum	20°C	10°C	10%
Maximum	49°C	49°C	85%

Drying Time

Surface Temperature	Surface Dry	Hard Dry	Full Cured
25°C	3.5 hour	7 hours	7 days

Determined based on wet film thickness 76 μ at standard conditions.

Storage Condition

Keep away from heat, fire and direct sunlight. Close the container tightly when not in use, keep in dry and cool room. Keep in temperature room (25-30 degree C).

Shelf-Life Product

Standard shelf life is 24 months from the date of manufacturing in originally not opened boxes, but may be extended based upon retesting by Pacific Paint Quality Control.

Health, Safety and Environment

Always use personal protective equipment and apply in a well-ventilated space. Caution with hazard symbol, see on packaging or refer to safety data sheet.

Read all safety, security, health and environment precautions before use. Wash hands and exposed skin before meals and after use. In case of contact with eyes and skin, rinse immediately with clean water, if swallowed or for more serious cases seek medical attention immediately.